

Product Description

TREMproof® PUMA Flashing System is a quick-cure, liquid-applied system based on PUMA technology. Components of the system can be initiated to cure within minutes, even in temperatures below freezing, and has tenacious adhesion to concrete and metal. TREMproof PUMA Flashing System is composed of a primer (Tremco PUMA Primer) and a UV stable base coat (Tremco PUMA Flashing). A top coat (Tremco PUMA TC) can be used when needed for aesthetic reasons. If there is a need for over burden or a connection with an adjacent product, please call Tremco Technical Service. All system components are cured using Tremco PUMA Initiator.

Tremco PUMA Primer is a methyl-methacrylate (MMA), two-component primer for porous and non-porous substrates.

Tremco PUMA Flashing is a modified polyurethane-methacrylate (PUMA) base coat. Tremco PUMA Flashing bonds firmly to Tremco PUMA Primer. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Tremco PUMA Flashing will prevent water migration between itself and the substrate.

Tremco PUMA TC is a methyl-methacrylate (MMA) top coat. Interlaminary adhesion to Tremco PUMA TC is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance.

Basic Uses

TREMproof PUMA Flashing System is a cold-applied flashing system designed for waterproofing penetrations, window flashings and block trails. Additionally, the system will protect the concrete from the damaging effects of chloride, deicing salts, chemicals, gasoline, oils and anti-freeze.

Features and Benefits

- Polyurethane-methacrylate (PUMA) technology delivers extreme durability while maintaining its crack-bridging characteristics.
- Rapid set-up times allow for quick overall installation, as well as the ability to open up to foot traffic one hour later.
- Can be applied at temperatures below 20 °F (-7 °C), which allows for continuation of projects in the colder months.
- Initiator adjustments allow for 30 to 45 min cure time between applications, even at temperatures below freezing.
- Compatible with Tremco sealants, coatings and hot rubberized asphalt, which is essential for tie-ins, detailing and penetrations.
- Extremely forgiving application allows users to apply additional coats long after the previous coat has cured.
- Unique chemistry allows for easy repair.

Availability

Immediately available from your local Tremco Sales Representative.

Packaging

Tremco PUMA Primer: 6-gal pails

Tremco PUMA Flashing: 2-gal pails

Tremco PUMA TC: 6-gal pails

Tremco PUMA Initiator: 22-lb or 55-lb pails

Tremco PUMA Cleaner: 6-gal pails

Colors

Tremco PUMA TC is available in Gray, Slate Gray, and Tintable.

Installation

Concrete shall be water-cured and attain a 3000 PSI minimum compressive strength for waterproofing applications, 4000 PSI for vehicular traffic. Concrete finish shall be an equivalent ICRI #3-#4 finish. Moisture content in the concrete must be lower than 6% as measured using a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical representative.

Please refer to the TREMproof PUMA for Flashing Application Instructions for complete application details. The techniques involved may require modification to adjust to job-site specific conditions. Consult your Tremco Sales Representative or Tremco Technical Services for site conditions and requirements.

Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TREMproof® PUMA EWS Flashing System

Quick-Cure, Liquid-Applied Flashing based on PUMA Technology

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TREMCO PUMA FLASHING	TREMCO PUMA TC
VOC Content	Method 310	0 g/L	0 g/L
% Solids (by Weight)	ASTM D1353	100%	100%
Drying Time @ 75°F, 50% RH	ASTM D1640	80 mil film, 1 hr	17 mil film, 1 hr
Weathering	ASTM D822 Weatherometer 350 hr	N/A	No effect
Elongation	ASTM D638	407% - 420%	130%
Elongation	ASTM D5147	Min 30%	Min 30%
Tensile Strength	ASTM D638 @ 75°F	991 - 1680 psi	986 psi
Tearing Resistance	ASTM D4073	91 lbf	203 lbf
Hardness (Shore D)	ASTM D2240	18 - 35	55
Hardness (Shore A)	ASTM D2240	65 - 87	100
Abrasion Resistance (1000 cycles)	ATSM D4060	N/A	51 mg
Low-Temperature Crack Bridging	ASTM C1305	Passes	N/A
Taber Abrasion	ASTM C501	Passes	N/A
Peak Load @ 73°F, avg.	ASTM D5147	>70 lbf/in	238 lb/in
Puncture Resistance	ASTM D5602	> 56 lbs	>56 lbs
Water Absorption	ASTM D570	< 0.1%	< 0.1%
Water Vapor Transmission	ASTM E96	0.03 perms	0.03 perms
Adhesion-in-Peel	ASTM C794	Concrete failure with primer	N/A
Self-Ignition Temperature	ASTM D1929	800 °F (427 °C)	850 °F (454 °C)
Smoke Density	ASTM D2843	4.1%	2.1%
Rate of Burn	ASTM D635	1.2 in/min	0.2 in/min
Adhesion-in-Peel	ASTM C794	≥ 1 pli	≥ 1 pli

0401/TPFSDS

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555

www.tremcosealants.com

